

POLYLAC OPAQUE



Fine, opaque enamel paint for interiors.

Colours	White and black
Packaging	0.375 – 0.750 – 2.5 litres
Product characteristics	
Composition	Based on alkyd resins and selected pigments.
Specific weight	White 1.300 – 1.350 kg/l. Black 1.240 kg/l.
Percentage weight of dry resin of the total dry weight content	48% \pm 2.
Drying time	Dry: 2 – 3 hours. Hardened: 16 – 24 hours
Recoatable	After 16 hours.
Spreading rate	14 – 16 sqm/litre per coat.
Coverage	Excellent.
Filling	Good.
Average thickness of applied film	20 – 30 micron per coat.
Film aspect	Opaque gloss 9 – 11 on 60° gloss meter.
Storage	In tightly sealed cans.

Instructions for use

Use	On wood, iron, window shutters, doors, furniture and radiators.
Application	Brush or roller.
Dilution	Ready to use.
Cleaning of equipment	With Diluente Sintetico 914090L.

Warning

Work in a well ventilated area, wearing appropriate personal protective equipment (such as a mask). Sanding, welding and flame removing old paint can generate dust and/or hazardous fumes.

Application systems	<p>A) New iron:</p> <ul style="list-style-type: none"> - Allow the iron to rust in order to facilitate removal of the calamine. - Brush and/or sand to remove any rust present. - Apply two coats of Metallite, diluted 5% by volume with Diluente Sintetico 914090L. - Apply two coats of undiluted Polylac Opaque. <p>B) Old painted iron:</p> <ul style="list-style-type: none"> - Brush and/or sand to treat the rusted parts and to remove any old coats of paint not well adhering. - Touch up the points with undiluted Metallite. - If the rust is extensive, apply one coat of Metallite over the entire surface, diluted up to a max of 5% by volume with Diluente Sintetico 914090L. - Apply two coats of undiluted Polylac Opaque. <p>C) New wood:</p> <ul style="list-style-type: none"> - Sand accurately. - Apply one coat of undiluted Opaco G9. - Sand again. - Apply one coat of undiluted Polylac Opaque. <p>D) Painted wood:</p> <ul style="list-style-type: none"> - Sand accurately and thoroughly to remove old coats of paint not well adhering and to roughen the surface. - Apply one coat of undiluted Opaco G9. - Sand again. - Apply two coats of undiluted Polylac Opaque.
---------------------	--

Note

It is not recommended for application on substrates containing a high percentage of humidity. Wait at least 18 hours between coats.

Product specification

Opaque, solvent based enamel paint for interiors (such as Polylac Opaque); based on alkyd resins and selected pigments.

Mean specific weight	White 1.300 – 1.350 kg/l. Black 1.240 kg/l.
Percentage weight of dry resin of the total dry weight content	48% ± 2.
Film aspect	Opaque gloss 9 – 11 on 60° gloss meter.

All technical information contained herein is indicative.

For more detailed information, please consult our TECHNICAL SERVICE DEPARTMENT.